

# Bioplastic From Renewable Resource: Utilization Of Orange Peel Cellulose And Pearl Millet Pectin For Anti-Biofilm Properties ----- A Review

Sreya Balakrishnan<sup>1</sup>, K Arungandhi<sup>2\*</sup>

<sup>1,2\*</sup>Department of Biotechnology, Dr.N.G.P Arts and Science College, Kalapatti, Coimbatore, India

**\*Corresponding author:** K Arungandhi

\*Email: arungandhi@drngpasc.ac.in

## ABSTRACT

Plastics are widely used everywhere such that in packing of food, substance and also they are harmful for environment. This is because it is versatile, durable and easy to carry. Plastic are non-biodegradable waste and cause pollution for environment. So to resolve the problem we can use bioplastic biodegradable films etc. The development of biodegradable films can decrease its use such a way that now food industries, textile industries, etc. Use biodegradable films as alternative. Biodegradable films are thin, flexible materials that can decompose naturally in the environment, typically within a few months to a few years. The increasing demand for sustainable and eco-friendly materials has led to the exploration of alternative sources for biodegradable films. Orange peel and Pearl millet are two agricultural waste materials that have shown promise in this regard. The isolation of cellulose from orange and pectin from pearl millet. The film is been produced by both cellulose and pectin which is been coated with PVA, its anti-biofilm activity is been tested. Highlights the challenges and future prospects of using these materials in bioplastic. Bioplastic are used in packaging, agriculture, and medicine, providing a sustainable alternative to traditional plastics. Biodegradable films are designed to provide a physical barrier or packaging solution. Thereby material can be recycled and reuse to make it innovative, and production of plastic will be reduced and pollution will be decreased.

**Keywords:** Orange peel, Cellulose, Pearl Millet, Pectin, Biodegradable film, Anti-biofilm activity, food packaging.


## INTRODUCTION

Over the previous century, the production of plastics has grown significantly; in 2015, Statista A. M. Balu et al., (2012) started that 322 million tons were produced worldwide. By now, the enormous quantity of plastic products—which are usually derived from non-renewable resources—has resulted in significant plastic pollution. Conversely, biodegradable or renewable resources are used to make bioplastics; in the best instance, both are true. Although farmed crops are being employed to generate biopolymers, very little land is still utilized for bioplastic. Citrus waste serves as an illustration of a bio based and biodegradable substance composed of several biopolymers that has no land use purpose. A plentiful and environmentally problematic waste that is underutilized worldwide is citrus trash. The most widely cultivated tropical fruit among citrus fruits is the sweet orange. According to USDA, 45.8 million tons of sweet oranges would be produced in 2015–16. In the case of orange juice production, for instance, industrial orange processing leaves behind between 50 and 60 percent of the orange's initial bulk. This enormous amount of garbage has a low pH (3–4), is high in water (about 80–90%) and organic matter (approximately 95% of total solids), and improper treatment could seriously harm the environment. Additionally, orange trash has pectin, soluble sugars, cellulose, hemicelluloses, starch, protein, lignin, ash, fat, and flavonoids, all of which have been demonstrated to be advantageous for a variety of inefficient disposal and recovery applications A. F. Routh et al.,(2013). In contrast, these chemicals may be useful for applications using bioplastics. Orange trash has previously been used as reinforcement in bio based or petrochemical matrices. The authors noted improved mechanical qualities of the products in each of these instances as compared to the clean polymer. The current cellulosic fibres are most likely directly responsible for the improved mechanical qualities. Pectin, the main ingredient in pearl millet, appears to have no discernible impact on the aforementioned composites, nevertheless. However, several reinforcing materials have been used to create pectin-based composites, and cellulosic plant fibres have garnered a lot of attention due to their advantageous mechanical qualities as a possible glass fibre replacement in bio-composites. For instance, commercially available cellulose reinforced pectin composites have been created for use in food packaging and tissue engineering. There isn't any research on creating a biofilm directly from cellulosic fibres from orange trash and pectin derived from pearl millet. This study examined the process of turning orange garbage into a bio-based film and assessed its characteristics. As a result of our work, a new purpose was given to orange waste and biofilms were produced without prior chemical modification of the raw material A. Soroudi et al., (2013). Film casting was used to prepare the films. Orange waste has mechanical qualities that are competitive with those of some commodity plastics and is derived from plants and biodegradable. Therefore find usage in non-structural applications with additional advancements, such as a sustainable packaging material for the food industry.

## Orange Waste

Among the most widely consumed citrus crops worldwide is the orange. This fruit contains a number of beneficial substances, including flavonoids, catechins, antioxidants, folic acid, and vitamin C. Because oranges can be grown in a variety of soil types and climates, they are regarded as a crop that is adaptable. Oranges can be grown in a number of nations between Ecuador's north and south, between 30° and 35°. Orange peel has 11% hemicellulose, 22% cellulose,

25% pectin's, and 23% sugar Santi G et al., (2014). These values make biochemical transformations, like the creation of bioethanol or biogas, viable possibilities. The full application of these procedures necessitates substantial research because they need multiple steps of biomass treatment, each of which may produce a by-product.



### Pearl Millet

Pearl millet is primarily grown in arid and semi-arid regions of Africa and Asia. Its processing generates significant by-products, including bran and hulls, which contain pectin substances that can be extracted and utilized in various applications. The pectin content in pearl millet hulls and bran is influenced by several factors, including maturity, variety, and growing conditions. Pearl millet pectin is primarily composed of galacturonic acid, rhamnose, arabinose, and galactose, similar to pectin obtained from conventional sources. Several studies indicate that pearl millet hulls contain a considerable amount of pectin, making them a potential raw material for sustainable pectin production.

### Cellulose

A 1:15 ratio of 5% (w/v) sodium hydroxide (NaOH) heated at around 80 °C for three hours was used to achieve the alkaline treatment. The cellulose underwent a 10-minute centrifugation at 3500 rpm and multiple washes with distilled water to achieve a pH of neutral. The fibres were then bleached at a fibre to solvent ratio of 1:15 using 1.7% (w/v) NaClO<sub>2</sub>. The mixture was heated to roughly 80 °C for two hours after being acidified to pH 4 with the addition of glacial acetic acid. And then heated for 5 hours and then collect the sediment and then dry the sediment. Cellulose is been extracted.

### Pectin

Pectin is been extracted from pearl millet for that first for that we should weigh 15g and heat for 30mins at 80°C then we should filter the extract and then add 95% ethanol and then keep it for 30mins for observation after that centrifuge the extract at 3000rpm for 10mins and then collect the pellet and then dry in hot air oven in a petri plate. The most popular aqueous extraction techniques for pectin include direct boiling, microwave heating, ultrasonic, autoclaving, and electromagnetic induction. All these pectin extraction techniques contribute to the degrading of pectin quality to some degree. Variations in temperature, extraction duration, pH, and source material all affect pectin output.

### Bioplastic

Plastic is a packaging material used for household needs, wrapping food and drinks and other necessities, because plastic is light and the price is affordable, but in its use, plastic has a negative impact on environmental sustainability because plastic is difficult to degrade. Several studies have been carried out to reduce the use of plastic or replace it with environmentally friendly packaging, namely biodegradable plastic or bioplastic. Bioplastics are plastics that can be degraded in a short time made of natural polymer materials such as starch, cellulose and fat and the main ingredients that are often used in the manufacture of biodegradable plastics are starch and Poly Lactic Acid (PLA). In addition, as one of the uses in processing bioplastics, also be made from cellulose and pectin which is been extracted from orange peel waste and pearl millet.

### Physical Properties of Bioplastic

A sustainable substitute for traditional plastics, bioplastic made from leftover cellulose from orange peels and pearl millet pectin combines strength, flexibility, and biodegradability. The proportion of cellulose to pectin affects this bioplastic's mechanical qualities; cellulose gives it structural rigidity and tensile strength, while pectin improves its flexibility and film-forming capacity. While the elongation at break varies based on the composition, usually between 10 and 50 percent, the moderate tensile strength makes it appropriate for flexible packaging applications. The material's glass transition temperature (T<sub>g</sub>) ranges from 50 to 150°C, depending on the amount of cellulose and pectin present. Thermal breakdown happens at temperatures higher than 200°C. In contrast to synthetic polymers, the bioplastic has a low melting point but strong thermal stability. Although the inclusion of cellulose marginally increases moisture resistance, the material's high pectin concentration renders it hydrophilic, resulting in water absorption between 20 and 60%. This makes the bioplastic appropriate for short-term uses but less suitable for extended exposure to humid conditions. Depending on the ratio of cellulose to pectin, the bioplastic might seem clear or opaque and have a smooth or somewhat rough feel. With a density

that is usually between 0.8 and 1.2 g/cm<sup>3</sup>, the material is lightweight and on par with traditional plastics. It is an environmentally beneficial substitute because of its high biodegradability, which breaks down in a matter of weeks to months when left to its own devices. The substance is resistant to mild acids and alcohols, but it breaks down in strongly acidic or alkaline settings. It is also somewhat water soluble and swells in high humidity. In line with the demand for sustainable material substitutes, these characteristics make bioplastic derived from orange peel cellulose and pearl millet pectin a viable option for biodegradable food packaging, disposable containers, agricultural mulch films, and edible films.

### Advantages of Bioplastics from Cellulose and Pectin

Bioplastic made from leftover cellulose from orange peels and pectin from pearl millet has a number of benefits that make it a sustainable and environmentally friendly substitute for traditional plastics. Its ability to break down naturally without leaving behind dangerous micro-plastics is one of its main advantages; this lowers pollution in the environment. In addition to being a renewable raw material, using orange peel waste cellulose helps manage waste by reusing agro-industrial wastes that would otherwise be thrown away. The biopolymer's structural integrity is also strengthened by pearl millet pectin, which also gives the bioplastic flexibility and better water resistance, making it appropriate for a variety of uses like food packaging and throwaway goods.

### Disadvantages of Bioplastic from Cellulose and Pectin

Although they provide environmentally beneficial alternatives, bioplastics derived from orange peel waste cellulose and pearl millet pectin have a number of drawbacks. First of all, it might be expensive and energy-intensive to separate cellulose from orange peel and pectin from pearl millet, which makes large-scale production economically difficult. Furthermore, because these bioplastics could not be as strong, flexible, or durable as traditional plastics, their mechanical qualities might not always satisfy the needs of specific applications. Another potential drawback is the scarcity of raw materials, as pearl millet and leftover orange peel may not be sufficient for large-scale manufacturing. Additionally, even though these bioplastics are biodegradable, in some situations they may break down too quickly, which would restrict their application in goods that need a longer shelf life. The effects of processing on the environment are also a concern; even though the materials are derived from waste products, large amounts of energy and resources may still be used during the extraction and refinement stages. Lastly, it is yet unknown how these bioplastics may affect the environment, human health, and performance in the long run due to a lack of thorough research on these topics.

### Conclusion

In conclusion, by using agricultural waste materials, bioplastics made from cellulose waste from orange peels and pectin from pearl millet offer a viable, sustainable substitute for traditional plastics. They have the potential to improve the environment by lowering plastic waste and being biodegradable. But obstacles like exorbitant manufacturing prices, scarce raw materials, and worries about their processing effects and mechanical characteristics prevent them from being widely used. To completely comprehend their long-term performance and environmental effects, more research is also required. Notwithstanding these limitations, bioplastics made from orange peel and pearl millet may prove to be a useful tool in the transition to more environmentally friendly materials with additional development and improvement.

### References

1. Statista, Global plastic production from 1950 to 2015 (in million metric tons), Statista, 2016.
2. E. Bioplastics, "Biobased plastics - Fostering a resource efficient circular economy; Benefits, feedstock types, sustainable sourcing, land use," in Proceedings of the 10th European Bioplastics Conference, Berlin, Germany: European Bioplastics, 2015.
3. A. M. Balu, V. Budarin, P. S. Shuttleworth et al., "Valorisation of orange peel residues: Waste to biochemicals and nanoporous materials," *ChemSusChem*, vol. 5, no. 9, pp. 1694–1697, 2012.
4. M. Boukroufa, C. Boutekedjiret, L. Petigny, N. Rakotomanomana, and F. Chemat, "Bio-refinery of orange peels waste: A new concept based on integrated green and solvent free extraction processes using ultrasound and microwave techniques to obtain essential oil, polyphenols and pectin," *Ultrasonics Sonochemistry*, vol. 24, pp. 72–79, 2015.
5. USDA, *Citrus: World Markets and Trades*, United States Department of Agriculture Foreign Agricultural Service, USA, 2016.
6. J. Angel Siles López, Q. Li, and I. P. Thompson, "Biorefinery of waste orange peel," *Critical Reviews in Biotechnology*, vol. 30, no. 1, pp. 63–69, 2010.
7. F. R. Marín, C. Soler-Rivas, O. Benavente-García, J. Castillo, and J. A. Perez-Alvarez, "By-products from different citrus processes as a source of customized functional fibres," *Food Chemistry*, vol. 100, no. 2, pp. 736–741, 2007.
8. K. Rezzadori, S. Benedetti, and E. R. Amante, "Proposals for the residues recovery: Orange waste as raw material for new products," *Food and Bioproducts Processing*, vol. 90, no. 4, pp. 606–614, 2012.
9. R. U. Abass, "Mechanical behaviour of natural material (orange peel) reinforced polyester composite," *International Journal of Engineering Sciences Research Technology*, vol. 4, no. 3, pp. 166–172, 2015.
10. V. S. Aigbodion, C. U. Atuanya, E. A. Igogori, and P. Ihom, "Development of High-Density Polyethylene /Orange Peels Particulate Bio-Composite," *Gazi University Journal of Science*, vol. 26, no. 1, pp. 107–117, 2013.
11. L. Shen, M.K. Patel, Life cycle assessment of polysaccharide materials: a review, *J. Polym. Environ.* 16 (2008) 154

12. H.P.S. Abdul Khalil, E.W.N. Chong, F.A.T. Owolabi, M. Asniza, Y.Y. Tye, S. Rizal, M.R. Nurul Fazita, M.K. Mohamad Haafiz, Z. Nurmiati, M.T. Paridah, Enhancement of basic properties of polysaccharide-based composites with organic and inorganic fillers: a review, *J. Appl. Polym. Sci.* 136 (2019), 47251,
13. Y. Zheng, J. Monty, R.J. Linhardt, Polysaccharide-based nanocomposites and their applications, *Carbohydr. Res.* 405 (2015) 23–32.
14. V.K. Varshney, S. Naithani, Chemical functionalization of cellulose derived from nonconventional sources, *Cellul. Fibers Bio- Nano-polymer Compos*, 2011
15. D. Klemm, B. Heublein, H.P. Fink, A. Bohn, Cellulose: fascinating biopolymer and sustainable raw material, *Angew. Chemie - Int. Ed.* (2005).
16. D.J. Cosgrove, Growth of the plant cell wall, *Nat. Rev. Mol. Cell Biol.* (2005).
17. D.J. Cosgrove, Expansive growth of plant cell walls, *Plant Physiol. Biochem.* (2000).
18. A.C. O'Sullivan, Cellulose: the structure slowly unravels, *Cellulose* (1997).
19. J. George, S.N. Sabapathi, Cellulose nanocrystals: synthesis, functional properties, and applications, *Nanotechnol. Sci. Appl.* (2015).
20. R.F. Nickerson, J.A. Habrle, Cellulose intercrystalline structure, *Ind. Eng. Chem.* (1947).
21. M.S. Reid, M. Villalobos, and E.D. Cranston, Benchmarking cellulose nanocrystals: from the laboratory to industrial production, *Langmuir* (2017).
22. J.F. Revol, H. Bradford, J. Giasson, R.H. Marchessault, D.G. Gray, Helicoidal selfordering of cellulose microfibrils in aqueous suspension, *Int. J. Biol. Macromol.* (1992).
23. T.D. Nguyen, E. Sierra, H. Eguiraun, E. Lizundia, Iridescent cellulose nanocrystal films: the link between structural colour and Bragg's law, *Eur. J. Phys.* (2018).
24. X. Mu, D.G. Gray, Formation of chiral nematic films from cellulose nanocrystal suspensions is a two-stage process, *Langmuir* (2014).
25. I.C. Gebeshuber, D.W. Lee, Nanostructures for coloration (organisms other than animals), *Encycl. Nanotechnol.*, 2016.
26. B.J. Glover, H.M. Whitney, Structural colour and iridescence in plants: the poorly studied relations of pigment colour, *Ann. Bot.* (2010).
27. S. Belbekhouche, J. Bras, G. Siqueira, C. Chappey, L. Lebrun, B. Khelifi, S. Marais, A. Dufresne, Water sorption behavior and gas barrier properties of cellulose whiskers and microfibrils films, *Carbohydr. Polym.* (2011).
28. L. Shen, M.K. Patel, Life cycle assessment of polysaccharide materials: a review, *J. Polym. Environ.* 16 (2008) 154.
29. H.P.S. Abdul Khalil, E.W.N. Chong, F.A.T. Owolabi, M. Asniza, Y.Y. Tye, S. Rizal, M.R. Nurul Fazita, M.K. Mohamad Haafiz, Z. Nurmiati, M.T. Paridah, Enhancement of basic properties of polysaccharide-based composites with organic and inorganic fillers: a review, *J. Appl. Polym. Sci.* 136 (2019), 47251.
30. Y. Zheng, J. Monty, R.J. Linhardt, Polysaccharide-based nanocomposites and their applications, *Carbohydr. Res.* 405 (2015) 23–32.